


Electrical Insulating Structural Shapes

Angles and Channels

Glastic Electrical Insulating Structural Products

- Grade UTR Pultrusions
- Dimensions are in inches
- All parts are available in standard lengths of 120 inches except 2261 and 2890



CHANNEL			
PART NO.	WIDTH	LEG	THICKNESS
2875	2	9/16	1/8
2617	2	13/16	1/8
1144	2	1	1/4
2261	2-3/16	3/4	1/16
2212	2-5/16	3/4	1/8
1177	2-9/16	1-7/32	1/8
1166	3	7/8	1/4
2888	3	1-1/2	1/4
1939	3-9/16	2-9/16	3/16
1791	3-19/32	1-1/8	1/8
1155	4	1-1/8	1/4
2242	4	1-3/8	3/16
2872	4-1/2	2-1/2	1/8
2874	4-1/2	2-1/2	1/4
1940	4-9/16	2-9/16	9/32
1788	4-3/4	1-5/8	3/16
2825	5-1/2	1-1/4	5/32
2288	6-3/8	2	9/32
1844	8-1/2	2-11/16	3/16
1936	9-21/32	1-5/8	1/8
2250	11-9/32	1-5/8	3/8
2120	11-1/2	1-7/16	5/32

HAT SHAPED CHANNEL			
PART NO.	WIDTH	LEG	THICKNESS
1161	4-19/32	7/8	1/8
2091	5	1-3/8	1/8
1272	9-9/16	2-3/8	3/16

EQUAL LEG ANGLES			
PART NO.	LEG A	LEG B	THICKNESS
2889	1-1/4	1-1/4	1/8
2879	1-1/4	1-1/4	3/16
2880	1-1/2	1-1/2	1/8
2881	1-1/2	1-1/2	3/16
2882	1-1/2	1-1/2	1/4
2883	2	2	3/16
2884	2	2	1/4
2885	3	3	1/4
2886	3	3	3/8

UNEQUAL LEG ANGLES			
PART NO.	LEG A	LEG B	THICKNESS
1134 *	1-3/4	2	3/8
2891	2	2-3/4	1/2
2876	2-1/4	1-1/2	3/16
1133	2-1/2	1-1/4	3/16
2877	2-3/4	2	1/4
2890	6	3	1/2

*Also sold in 7' lengths.

TERMINAL STRIPS			
PART NO.	HEIGHT	WIDTH	THICKNESS
2700	3/8	1-1/4	1/8
2710	7/16	1-1/2	1/4
2720	----	2	1/2

SQUARE TUBE			
PART NO.	HEIGHT	WIDTH	WALL THICKNESS
F822024	1-1/2	1-1/2	1/8
F822432	2	2	1/4

Electrical Insulating Structural Shapes

Angles and Channels

GENERAL INFORMATION	UNIT	ASTM/UL TEST NUMBER	TYPICAL AVERAGE ¹ VALUES
Color	----	----	Red
NEMA Grade	----	----	GPO-3
UL Recognition File Number	----	----	E 23525
MECHANICAL PROPERTIES			
Tensile Strength	Psi	D638	15,000
Tensile Modulus	Psi x 10 ⁶	D638	1.7
Flexural Strength	Psi	D790	25,000
Flexural Strength at 130° C	Psi	D790	13,000
Flexural Modulus	Psi x 10 ⁶	D790	1.2
Compressive Strength-flatwise	Psi	D695	42,000
Compressive Strength-edgewise	Psi	D695	20,000
Shear Strength	Psi	D732	14,500
IZOD Impact Strength (notched)	Ft.lb./in.	D256	9.6
Water Absorption	% by Wgt.	D570	0.3
Barcol Hardness	----	D2583	50
Specific Gravity	----	D792	1.8
ELECTRICAL PROPERTIES			
Electric Strength – perpendicular s/t in air ²	Vpm	D149	200
Electric Strength – parallel	kV	D149	45
Arc Resistance	Sec.	D495	185
Inclined Plane Track Resistance	Min.	D2303	500+
FLAME RESISTANCE PROPERTIES			
UL Subject 94	----	UL94	VO
THERMAL PROPERTIES			
Coefficient of Thermal Expansion	In/in/° C x 10 ⁻⁵	D696	2.0
Thermal Conductivity	BTU/hr/Ft ² /in/° F	C177	1.9
UL Temperature Index			
Electrical	° C	UL746B	130
Mechanical	° C	UL746B	160
DIMENSION TOLERANCES			
Thickness			
Up to .125 in.	in.	----	±.015
.125 in. to .250 in.	in.	----	±.020
over .250 in.	in.	----	±.025
Angularity of Legs	Degrees	----	±3
Cut Length	in.	----	+0.5, -0



GLASTIC CORPORATION

4321 Glenridge Road | Cleveland, OH 44121-2891 | phone 216-486-0100 | toll free 800-360-1319 | fax 216-486-1091 | www.glastic.com

All of the information, suggestions, and recommendations pertaining to the properties and uses of the Glastic products described herein are based upon tests and data believed to be accurate; however, the final determination regarding the suitability of any material described herein for the use contemplated, the manner of such use, and whether the use infringes any patents is the sole responsibility of the user. **THERE IS NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** Under no circumstances shall we be liable for incidental or consequential loss or damage.

Glastic® is a registered trademark of Glastic Corporation. UL® is a registered trademark of Underwriters Laboratories, Inc. ©2002 Glastic Corporation. All Rights Reserved. Printed in USA GL-1080B 0105